

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/GB05/000700

International filing date: 25 February 2005 (25.02.2005)

Document type: Certified copy of priority document

Document details: Country/Office: GB
Number: 0404535.7
Filing date: 01 March 2004 (01.03.2004)

Date of receipt at the International Bureau: 01 April 2005 (01.04.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse



PCT/GB05/00700

INVESTOR IN PEOPLE


The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Stephen Hordley

Dated

21 February 2005

11

12

13

14



Patents Form 1/77

PATENT OFFICE
PEPatents Act 1997
(Rule 16)

01 MAR 2004

RECEIVED BY FAX

**The
Patent
Office**

02MAR04 E877236-1 D02877

P01/7700 0.00-0404535.7 ACCOUNT CHA

1/77

Request for grant of a patent*(see the notes on the back of this form. You can also get an explanatory leaflet from the Patent office to help you fill in this form)*

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

- 1 MAR 2004

UQI 51127/GB

1 Your reference

2 Patent application number
(The Patent Office will fill in this part)

0404535.7

3 Full name, address and postcode of the or of
each applicant (underline all surnames)Imperial Chemical Industries plc
20 Manchester Square
London
W1U 3AN

Patents ADP Number (if you know it)

0400003585

00000935006

If the applicant is a corporate body, give the
country/state of its incorporation

United Kingdom

4 Title of the invention

Antiwear Automotive Formulations

5 Name of Your Agent (if you have one)

RALPH, Julie Diane

"Address for service" in the United Kingdom
to which all correspondence should be sent
(including the postcode)Uniqema Intellectual Property Dept
Wilton Centre, Wilton
Redcar
Cleveland
England, TS10 4RF

Patents ADP Number (if you know it)

07896889002

6 If you are declaring priority from one or more
earlier patent applications, give the country
and the date of filing of the or each of these

Country	Priority Application number (if you know it)	Date of Filing (day / month / year)
---------	---	--

7 If this application is divided or otherwise derived from an
earlier UK application, give the number and filing date of
the earlier application

Number of earlier application	Date of Filing (day / month / year)
-------------------------------	--

8 Is a statement of inventorship and of right to grant of a
patent required in support of this request?

Yes

Answer yes if:

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See Note (d)

Patents Form 1/77

Patents Form 1/77

- 9 Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form	-
Description	11
Claim(s)	3
Abstract	-
Drawings	-


- 10 If you are also filing any of the following state how many against each item

Priority documents	
Translations of priority documents	
Statement of Invention and right to grant of a patent (Patents Form 7/77)	
Request for Preliminary Examination and search (Patents Form 9/77)	
Request for Substantive Examination (Patents Form 10/77)	
Any other documents (Please specify)	

11

I/We request the grant of a patent on the basis of this application

Signature



Date

1 Mar 2004

- 12 Name and daytime telephone number of person to contact in the United Kingdom

Julie Diane RALPH
01642 435334

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been issued, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Patents Form 1/77

UQIS1127/GB

1

ANTIWEAR AUTOMOTIVE FORMULATIONS

The present invention relates to automotive engine oils comprising a base oil and an antiwear additive system comprising an ester and preferably further comprising a phosphorus-containing and/or sulphur-containing antiwear additive and the use of automotive engine oils comprising the antiwear additive system.

The automotive industry is under pressure to meet higher engine oil performance requirements whilst at the same time lowering emissions. The International Lubricant Standardisation and Approval Committee (ILSAC) GF-4 requirements for automotive engine oil have just been published. One key area where the specification has been tightened is the level of phosphorus. This is because phosphorus has been identified as a catalyst poison for the catalysts that are used in emission control systems. The allowed phosphorus level will now be a maximum of 0.08% by weight in the automotive engine oil, which is a 20% reduction from the level set in the GF-3 requirements. However ILSAC's original aim was a maximum allowed phosphorus level of 0.05%, which is indicative of future legislation reducing the proposed 0.08% level further.

It is expected that focus will now move to other elements in the engine oil, as well as phosphorus, that could impact emission control systems. For example sulphur is known to poison deNOx catalysts and ash residues from metals are known to plug after-treatment particulate traps.

Antiwear protection in modern automotive engine oils is mainly provided by the additive zinc dialkyl dithiophosphate (ZDDP), which contains phosphorus, sulphur and zinc. It is believed that the ZDDP degrades at potential wear points in the engine to form a polyphosphate glassy film which protects the potential wear points. The ZDDP is typically supplied as a concentrated solution (typically 80-100% ZDDP) in mineral oil. At current use levels (typically 0.5-1.5% of ZDDP solution) it is believed that ZDDP accounts for more than two thirds of the sulphur and all of the zinc and phosphorus present in engine oils. It is clear that this additive has a major effect on the emission control systems and as such the use of alternative antiwear additives needs to be explored.

35

The engine test requirements of the ILSAC GF-4 specification include the Sequence IVA test. This test is designed to evaluate an oil's ability in preventing camshaft lobe

UQ151127/GB

2

wear in slider valve train design engines operated at low-temperature, short-trip, "stop-and-go" conditions. One of the key pass/fail criteria of the test is that the average cam wear cannot be greater than 90 μm . Therefore any alternatives to ZDDP must at least meet the Sequence IVA pass/fail criteria whilst also providing a reduction in metal, phosphorus and/or sulphur levels.

ZDDP is also known to function as an oxidation inhibitor when used as an additive in an automotive engine oil. Therefore any alternatives to ZDDP must also exhibit oxidation inhibition properties.

10

Investigations undertaken by the inventors have led to the identification of an ester which is suitable to be used in an antiwear additive system, either by itself or to be used in conjunction with a reduced level of a phosphorus and/or sulphur containing antiwear additive in automotive engine oils. The antiwear additive system of the invention not only has reduced metal, phosphorus and sulphur levels but surprisingly also can provide antiwear properties that are superior to those of commercial antiwear additives in automotive engine oils. Furthermore the antiwear additive system of the invention exhibits oxidation inhibition properties.

According to the present invention, an automotive engine oil comprising a base oil and an antiwear additive system comprising an ester which is the reaction product of

- (a) at least one polyfunctional alcohol;
- (b) a dimer fatty acid; and
- (c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms

with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm^2/s and a non-polarity index (NPI)

$$\text{NPI} = \frac{\text{total number of carbon atoms} \times \text{molecul. weight}}{\text{number of carboxylate groups} \times 100}$$

of at least 500.

the automotive engine oil

The term automotive engine oil includes both gasoline and diesel (including heavy duty diesel) engine oils.

the base oil

UQI51127/GB

4

is preferably less than 5%, more preferably in the range from 0.1 to 3%, particularly 0.3 to 2%, and especially 0.5 to 1% by weight.

optionally at least one of an aliphatic dicarboxylic acid, an aliphatic monocarboxylic acid, and an aliphatic monofunctional alcohol.

Examples of suitable aliphatic dicarboxylic acids include glutaric, adipic, pimelic, suberic, azelaic, sebacic, undecanedioic, dodecanedioic, tridecanedioic, tetradecanedioic, pentadecanedioic, hexadecanedioic acids and mixtures thereof. The aliphatic dicarboxylic acid preferably has from 7 to 16 carbon atoms, more preferably from 8 to 14 carbon atoms. The aliphatic dicarboxylic acid is preferably linear. Azelaic acid, sebacic acid and dodecanedioic acid are particularly preferred. Azelaic acid is especially preferred.

The monoacid or monoalcohol, may be used to react with any OH or COOH groups respectively which remain unreacted after reaction between the polyfunctional alcohol and the dimer fatty acid and optionally the aliphatic dicarboxylic acid. Examples of the at least one aliphatic monocarboxylic acid include the saturated straight chained acids of pentanoic, hexanoic, heptanoic, octanoic, nonanoic, decanoic, undecanoic, dodecanoic, tridecanoic, tetradecanoic, pentadecanoic, hexadecanoic, heptadecanoic, octadecanoic, arachidic, behenic and lignoceric acids and mixtures thereof. Examples also include unsaturated and/or branched variants of the disclosed saturated, straight-chained acids. The at least one aliphatic monocarboxylic acid preferably has 7 to 20 carbon atoms, more preferably 8 to 18 carbon atoms. It may be branched or straight chained and preferably is saturated. Particularly preferred monoacids are a mixture of octanoic and decanoic acids, and isostearic acid.

Examples of the aliphatic monofunctional alcohol include pentanol, hexanol, heptanol, octanol, nonanol, decanol, undecanol, dodecanol, tridecanol, tetradecanol, pentadecanol, hexadecanol, heptadecanol, octadecanol and mixtures thereof. Examples also include unsaturated and/or branched variants of the disclosed saturated, straight chained acids. The aliphatic monofunctional alcohol preferably has 7 to 16 carbon atoms, more preferably 8 to 14 carbon atoms. It may be branched or straight chained and preferably is saturated. 2-Ethylhexanol is particularly preferred.

The resultant ester preferably has a kinematic viscosity at 100°C of 900 to 4000, more preferably 1100 to 3500, especially 1500-2500 mm²/s.

UQ151127/GB

3

The base oil of the automotive engine oil may be chosen from any of the Group I to Group VI base oils as defined by the American Petroleum Institute (API). The base oil may be a mixture of Group I to Group VI base oils.

5 at least one polyfunctional alcohol

The at least one polyfunctional alcohol is preferably a polyol. The polyol preferably is of formula $R(OH)_n$ where n is an integer, which ranges from 1-10 and R is a hydrocarbon chain, either branched or linear, more preferably branched, of 2 to 15 carbon atoms. The polyol is suitably of low molecular weight, preferably in the range
10 from 50 to 650, more preferably 60 to 150, and particularly 60 to 100. Examples of suitable polyols include ethylene glycol, propylene glycol, trimethylene glycol, diols of butane, neopentyl glycol, trimethylol propane and its dimer, pentaerythritol and its dimer, glycerol, inositol and sorbitol. Preferably the polyol is a neopentyl polyol. Preferred examples of neopentyl polyols are neopentyl glycol, trimethylol propane
15 and pentaerythritol. Preferably the neopentyl polyol comprises at least 50% by weight of neopentyl glycol, more preferably at least 70%, even more preferably at least 90%.

dimer fatty acid

The term dimer fatty acid is well known in the art and refers to the dimerisation
20 product of mono- or polyunsaturated fatty acids and/or esters thereof. Preferred dimer fatty acids are dimers of C10 to C30, more preferably C12 to C24, particularly C14 to C22, and especially C18 alkyl chains. Suitable dimer fatty acids include the dimerisation products of oleic acid, linoleic acid, linolenic acid, palmitoleic acid, and elaidic acid with oleic acid being particularly preferred. The dimerisation products of
25 the unsaturated fatty acid mixtures obtained in the hydrolysis of natural fats and oils, e.g. sunflower oil, soybean oil, olive oil, rapeseed oil, cottonseed oil and tall oil, may also be used. Hydrogenated, for example by using a nickel catalyst, dimer fatty acids may also be employed.

30 In addition to the dimer fatty acids, dimerisation usually results in varying amounts of oligomeric fatty acids (so-called "trimer") and residues of monomeric fatty acids (so-called "monomer"), or esters thereof, being present. The amount of monomer can, for example, be reduced by distillation. Particularly preferred dimer fatty acids used in the present invention, have a dimer content of greater than 50%, more preferably greater
35 than 70%, particularly greater than 85%, and especially greater than 94% by weight. The trimer content is preferably less than 50%, more preferably in the range from 1 to 20%, particularly 2 to 10%, and especially 3 to 6% by weight. The monomer content

UQIS1127/GB

5

The resultant ester preferably has a NPI value of at least 900, more preferably at least 1200 and especially at least 1500.

5 The resultant ester preferably has an average molecular weight of at least 3000, more preferably at least 4000 and especially at least 5000.

Preferred resultant esters include an ester which is the reaction product of a polyol, preferably a neopentyl polyol, more preferably neopentylglycol with dimer acid and an ester which is the reaction product of a polyol, preferably a neopentyl polyol, more
10 preferably neopentylglycol with dimer acid and a C5-C18 dicarboxylic acid, more preferably a C7-C16 dicarboxylic acid, particularly a C8-C14 dicarboxylic, especially azelaic acid.

15 The antiwear additive system preferably further comprises a phosphorus-containing and/or sulphur-containing antiwear additive.

The phosphorus-containing and/or sulphur-containing antiwear additive may also contain other inorganic elements such as nitrogen and halogens, in particular chlorine, boron and silicon. Furthermore it may contain metallic elements such as zinc,
20 molybdenum, tungsten and niobium.

Examples of phosphorus-containing additives include phosphate esters, acid phosphates, phosphites and dialkyl alkyl phosphonates. Examples of sulphur-containing additives include sulphurized olefins, sulphurized esters, sulphurized
25 aromatics, trithianes and derivatives of thioglycolates. Examples of phosphorus and sulphur-containing additives include dithiophosphates, thiophosphates and phosphorothionates. Preferred examples of a dithiophosphate are molybdenum dialkyl dithiophosphates and ZDDP with ZDDP being especially preferred. Examples of phosphorus and nitrogen-containing additives include phosphoramides and amine
30 phosphates. Examples of sulphur and nitrogen-containing additives include dithiocarbamates, for example molybdenum dithiocarbamates (MoDTC), ammonium salts of sulphonic acid, amine salts of thiocyanic acid, alkyl dithiobenzoxazoles, derivatives of 2-mercaptobenzothiazole and 2,5-dimercapto-1,3,4-thiadiazole. Examples of sulphur, phosphorus and nitrogen-containing additives include amine
35 thiophosphates and amine dithiophosphates.

UQ151127/GB

6

Preferably the phosphorus-containing and/or sulphur-containing antiwear additive contains both phosphorus and sulphur. More preferably the phosphorus-containing and/or sulphur-containing antiwear additive also contains zinc or molybdenum, particularly the phosphorus-containing and/or sulphur-containing antiwear additive is

5 ZDDP.

When the ester and the phosphorus-containing and/or sulphur-containing antiwear additive are both present in the antiwear additive system the ratio of ester to phosphorus-containing and/or sulphur-containing antiwear additive ranges from 80:20

10 to 20:80 weight percent, preferably from 70:30 to 30:70 and particularly from 60:40 to 40:60.

The antiwear additive system according to the invention has no more than 10 wt% phosphorus, preferably no more than 7wt%, more preferably no more than 6 wt%

15 phosphorus.

The antiwear additive system according to the invention is present at levels between 0.1 and 5 % by weight, more preferably between 0.3 and 4%, even more preferably between 0.5 and 3% in the automotive engine oil.

20

A preferred antiwear additive system comprises 0.5% by weight in the automotive engine oil of an ester which is the reaction product of neopentylglycol with dimer acid with 0.5% by weight in the automotive engine oil of a ZDDP solution (for example Lubrizol L1371). A further preferred antiwear additive system comprises 0.5% by

25 weight in the automotive engine oil of an ester which is the reaction product of neopentylglycol with dimer acid and azelaic acid with 0.5% by weight in the automotive engine oil of a ZDDP solution (for example Lubrizol L1371).

The automotive engine oil comprising the base oil and antiwear additive system

30 preferably has no more than 0.08 wt% phosphorus, more preferably no more than 0.07 wt%, especially no more than 0.06 wt% phosphorus present.

The automotive engine oil also comprises other types of additives of known functionality at levels between 0.1 to 30%, more preferably between 0.5 to 20 % more

35 especially between 1 to 10% of the total weight of the engine oil. These can include detergents, dispersants, oxidation inhibitors, corrosion inhibitors, rust inhibitors, friction modifiers, foam depressants, pour point depressants, viscosity index improvers and

UQI51127/GB

7

mixtures thereof. Viscosity index improvers include polyisobutylenes, polymethacrylate acid esters, polyacrylate acid esters, diene polymers, polyalkyl styrenes, alkenyl aryl conjugated diene copolymers and polyolefins. Foam depressants include silicones and organic polymers. Pour point depressants include

5 polymethacrylates, polyacrylates, polyacrylamides, condensation products of haloparaffin waxes and aromatic compounds, vinyl carboxylate polymers, terpolymers of dialkylfumarates, vinyl esters of fatty acids and alkyl vinyl ethers. Ashless detergents include carboxylic dispersants, amine dispersants, Mannich dispersants and polymeric dispersants. Friction modifiers include amides, amines and partial fatty

10 acid esters of polyhydric alcohols. Ash-containing dispersants include neutral and basic alkaline earth metal salts of an acidic organic compound. Oxidation inhibitors include hindered phenols and alkyl diphenylamines. Additives may include more than one functionality in a single additive.

15 According to a further embodiment of the present invention an antiwear additive system comprising an ester which is the reaction product of

(a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon

20 atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms

with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

$$\text{NPI} = \frac{\text{total number of carbon atoms} \times \text{molecul. weight}}{\text{number of carboxylate groups} \times 100}$$

25 of at least 500.

The antiwear additive system preferably further comprises a phosphorus-containing and/or sulphur-containing antiwear additive.

30 According to a further embodiment of the present invention a method of reducing wear in an automotive engine by the use of an automotive engine oil comprising a base oil and an antiwear additive system comprising an ester which is the reaction product of

35 (a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon

UQI51127/GB

8

atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

5
$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

of at least 500.

10 According to a further embodiment of the present invention use of an automotive engine oil comprising a base oil and an antiwear additive system comprising an ester which is the reaction product of

(a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

15
$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

20 of at least 500 to reduce wear in an automotive engine.

According to a further embodiment of the present invention the use of an antiwear additive system comprising an ester which is the reaction product of

25 (a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

30
$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

of at least 500 in an automotive engine oil.

35

UQI51127/GB

9

According to a further embodiment of the present invention a method of reducing wear in an automotive engine by the addition of an automotive engine oil comprising a base oil and an ester which is the reaction product of

(a) at least one polyfunctional alcohol;

5 (b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms

with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

of at least 500 wherein the automotive engine oil has a phosphorus level of no more than 0.08%.

15

According to a further embodiment of the present invention an automotive engine comprising an automotive engine oil comprising a base oil and an antiwear additive system comprising an ester which is the reaction product of (a) at least one polyfunctional alcohol;

20 (b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms

with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

25

$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

of at least 500.

30 The automotive engine comprising an automotive engine oil according to the invention exhibits a camshaft lobe wear, measured according to the Sequence IVA test, of not more than 90µm, preferably not more than 70µm, more preferably not more than 50µm, particularly not more than 40µm.

35 The automotive engine comprising an automotive engine oil according to the invention suffers wear resulting in a copper level in the automotive engine oil, measured at the end of the Sequence IVA test, of not more than 30ppm by weight, preferably not more

UQI51127/GB

10

than 20ppm, more preferably not more than 10ppm and especially not more than 5ppm.

5 The automotive engine comprising an automotive engine oil according to the invention suffers wear resulting in a copper level in the automotive engine oil, measured at the end of the Sequence IVA test, of not more than 90ppm by weight, preferably not more than 70ppm, more preferably not more than 50ppm and especially not more than 20ppm.

10 The invention will now be described further by way of example only with reference to the following Examples.

Example 1

15 The Sequence IVA Engine Test method was undertaken for a formulated automotive engine oil having as base oil a mixture of NexbaseTM 3060 and NexbaseTM 3043, (colourless, catalytically hydroisomerised and dewaxed base oils comprising of hydrogenated, highly isoparaffinic hydrocarbons – Group III base oil) with the addition of 1% by weight of different antiwear additive systems. The results are detailed in Table One.

20

Table One

Antiwear additive System	Ester/ZDDP solution A (50/50)	ZDDP solution B (comparative)	No additive (comparative)
Cam nose wear (μm)	4	11.9	55.7
Cam lobe wear (μm)	24.1	56.4	393.2
Viscosity unused oil (at 40°C in mm^2/s)	68	70.8	66.4
Viscosity used oil (at 40°C in mm^2/s)	52.9	52.4	52.8
Zn content (ppm)	533	>900	7
Fe content (ppm)	10	58	431
Cu content (ppm)	1	3	1

UQI51127/GB

11

The ester is the reaction product of neopentylglycol (167kg) with dimer acid with at least 95% dimer present (833kg) and C9 dicarboxylic acid (12.5kg). The ester has a viscosity at 100°C of about 2000 mm²/s and an NPI of typically greater than 2500.

The ZDDP solution A is Lubrizol L1371.

5 The ZDDP solution B is Infineum C9417

The automotive engine oil with ZDDP as antiwear additive system contains 0.1% phosphorus. The automotive engine oil with the ester/ZDDP blend as the antiwear additive system contains 0.05% phosphorus.

10

The data in Table 1 clearly illustrates that an antiwear additive system according to the present invention has significantly reduced cam lobe and cam nose wear as compared to the commercially available ZDDP and has much lower phosphorus, sulphur and metal content. Also the minimal change in the viscosity of the oil at 40°C

15 is indicative of the oxidative stability of the automotive engine oil.

20

25

30

35

UQI51127/GB

12

Claims

1. An automotive engine oil comprising a base oil and an antiwear additive system comprising an ester which is the reaction product of
- (a) at least one polyfunctional alcohol;
- 5 (b) a dimer fatty acid; and
- (c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms
- with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to
- 10 5000 mm²/s and a non-polarity index (NPI)
- $$\text{NPI} = \frac{\text{total number of carbon atoms} \times \text{molecul. weight}}{\text{number of carboxylate groups} \times 100}$$
- of at least 500
- 15 2. A method of reducing wear in an automotive engine by the use of an automotive engine oil comprising a base oil and an antiwear additive system comprising an ester which is the reaction product of
- (a) at least one polyfunctional alcohol;
- (b) a dimer fatty acid; and
- 20 (c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms
- with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)
- 25
$$\text{NPI} = \frac{\text{total number of carbon atoms} \times \text{molecul. weight}}{\text{number of carboxylate groups} \times 100}$$
- of at least 500
3. Use of an automotive engine oil comprising a base oil and an antiwear additive
- 30 system comprising an ester which is the reaction product of
- (a) at least one polyfunctional alcohol;
- (b) a dimer fatty acid; and
- (c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an
- 35 aliphatic monofunctional alcohol having 5 to 24 carbon atoms
- with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

UQI51127/GB

13

$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

number of carboxylate groups x 100

of at least 500 to reduce wear in an automotive engine.

- 5 4. Use of an antiwear additive system comprising an ester which is the reaction product of

(a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

- (c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

- 15 number of carboxylate groups x 100

of at least 500 in an automotive engine oil.

5. A method of reducing wear in an automotive engine by the addition of an automotive engine oil comprising a base oil and an ester which is the reaction product of

(a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

- (c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an aliphatic monofunctional alcohol having 5 to 24 carbon atoms with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

$$\text{NPI} = \frac{\text{total number of carbon atoms} * \text{molecul. weight}}{\text{number of carboxylate groups} * 100}$$

number of carboxylate groups x 100

- 30 of at least 500 wherein the automotive engine oil has a phosphorus level of no more than 0.08%.

6. An antiwear additive system comprising an ester which is the reaction product of

35 (a) at least one polyfunctional alcohol;

(b) a dimer fatty acid; and

(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon

UQI51127/GB

14

atoms, an aliphatic monocarboxylic acid having 7 to 24 carbon atoms and an aliphatic monofunctional alcohol having 7 to 24 carbon atoms with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to 5000 mm²/s and a non-polarity index (NPI)

- 5 NPI = total number of carbon atoms * molec. weight
 number of carboxylate groups x 100
of at least 500.

7. An automotive engine comprising an automotive engine oil comprising a base oil
10 and an antiwear additive system comprising an ester which is the reaction product of
(a) at least one polyfunctional alcohol;
(b) a dimer fatty acid; and
(c) optionally at least one of an aliphatic dicarboxylic acid having 5 to 18 carbon
atoms, an aliphatic monocarboxylic acid having 5 to 24 carbon atoms and an
15 aliphatic monofunctional alcohol having 5 to 24 carbon atoms
with the resultant ester having a kinematic viscosity at 100 °C ranging from 500 to
5000 mm²/s and a non-polarity index (NPI)

- NPI = total number of carbon atoms * molec. weight
 number of carboxylate groups x 100
20 of at least 500.



